



PRESTATIEVERKLARING

fischer 
innovative solutions

Nr. 0072 – NL

1. Unieke identificatiecode van het producttype: **injectiesysteem fischer FIS V**

2. Beoogd(e) gebruik(en):

Product	Beoogd gebruik
Lijm anker te gebruiken in beton	Voor bevestigen van constructieve elementen of veiligheidsrelevante onderdelen zoals verlaagde plafonds aan beton, zie bijlage, in het bijzonder bijlagen B 1 tot en met B 10

3. Fabrikant: **fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Duitsland**

4. Gemachtigde: --

5. Het systeem of de systemen voor de beoordeling en verificatie van de prestatiebestendigheid: **1**

6a. Geharmoniseerde norm: ---

Aangemelde instantie(s): ---

6b. Europees beoordelingsdocument: **ETAG 001, 2013-04**Europese technische beoordeling: **ETA-02/0024; 2016-06-17**Technische beoordelingsinstantie: **DIBt**Aangemelde instantie(s): **1343 – MPA Darmstadt**

7. Aangegeven prestatie(s):

Mechanische weerstand en stabiliteit (BWR 1)

Essentieel kenmerk	Prestatie
Karakteristieke waarden voor statische en quasi statische belastingen voor ontwerp volgens TR 029 of CEN/TS 1992-4:2009, Verplaatsingen	Zie bijlage, in het bijzonder bijlagen C 1 tot en met C 10

Veiligheid bij brand (BWR 2)

Essentieel kenmerk	Prestatie
Brandgedrag	Verankeringen voldoen aan de vereisten voor klasse A1
Brand weerstand	Geen prestatie bepaald (NPD)

8. Geëigende technische documentatie en/of specifieke technische documentatie: ---

De prestaties van het hierboven omschreven product zijn conform de aangegeven prestaties. Deze prestatieverklaring wordt in overeenstemming met Verordening (EU) nr. 305/2011 onder de exclusieve verantwoordelijkheid van de hierboven vermelde fabrikant verstrekt.

Ondertekend voor en namens de fabrikant door:

Andreas Bucher, Dipl.-Ing.

Wolfgang Hengesbach, Dipl.-Ing., Dipl.-Wirtsch.-Ing.

Tumlingen, 2016-06-24

- Deze prestatieverklaring is opgesteld in verschillende talen. Bij een geschil over de interpretatie prevaleert de engelse versie.
- De bijlage bevat vrijwillige en aanvullende informatie in de Engelse taal boven op de (taal-neutraal gespecificeerde) wettelijke voorschriften.

Specific Part**1 Technical description of the product**

The injection system fischer FIS V is a bonded anchor consisting of a cartridge with injection mortar fischer FIS V and a steel element.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment**3.1 Mechanical resistance and stability (BWR 1)**

Essential characteristic	Performance
Characteristic values under static and quasi-static action for design according to TR 029 or CEN/TS 1992-4:2009, Displacements	See Annex C 1 to C 10

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorages satisfy requirements for Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

3.4 Safety in use (BWR 4)


The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with guideline for European technical approval ETAG 001, April 2013 used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


Installation conditions




Anchor rod
Pre-positioned anchor



Anchor rod
Push through anchor
(annular gap filled with mortar)



Reinforcing bar



fischer rebar anchor FRA
Pre-positioned anchor

fischer rebar anchor FRA
Push through anchor
(annular gap filled with mortar)

fischer injection system FIS V

Product description
Installation conditions

Annex A 1




Table A1: Materials

Part	Designation	Material		
1	Mortar cartridge	Mortar, hardener, filler		
	Steel grade	Steel, zinc plated	Stainless steel A4	High corrosion resistant steel C
2	Anchor rod	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 12 \%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$, EN ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
5	fischer internal threaded anchor RG MI	Property class 5.8 ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:1999 A2K	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
6	Screw or anchor / threaded rod for fischer internal threaded anchor RG MI	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:1999 A2K	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
7	Reinforcing bar EN 1992-1-1:2004 and AC:2010, Annex C	Bars and de-coiled rods, class B or C with f_{yk} and k according to NDP or NCL of EN 1992-1-1:2004+AC:2010 $f_{uk} = f_{tk} = k \cdot f_{yk}$		
8	fischer rebar anchor FRA	Rebar part: Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCL of EN 1992-1-1:2004+AC:2010 $f_{uk} = f_{tk} = k \cdot f_{yk}$	Threaded part: Property class 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529, 1.4401, 1.4404, 1.4571, 1.4578, 1.4439, 1.4362, 1.4062 EN 10088-1:2014	
fischer injection system FIS V				
Product description Materials				Annex A 3

Specifications of intended use (part 1)**Table B1:** Overview use and performance categories

Anchorage subject to		FIS V with ...								
		Anchor rod	fischer internal threaded anchor RG MI	Reinforcing bar		fischer rebar anchor FRA				
Hammer drilling with standard drill bit				all sizes						
Hammer drilling with hollow drill bit (Heller "Duster Expert" or Hilti "TE-CD, TE-YD")				Nominal drill bit diameter (d_0) 12 mm to 35 mm						
Static and quasi static load, in	uncracked concrete	all sizes	Tables: C1, C5, C6, C10	all sizes	Tables: C2, C5, C7, C11	all sizes	Tables: C3, C5, C8, C12	all sizes	Tables: C4, C5, C9, C13	
	cracked concrete	M10 to M30		not allowed		ϕ10 bis ϕ28				
Use category	dry or wet concrete			all sizes						
	flooded hole	M12 to M30	all sizes		not allowed		not allowed			
Installation temperature			-10 °C to +40 °C							
In-service temperature	Temperature range I	-40 °C to +80 °C	(max. long term temperature +50 °C and max. short term temperature +80 °C)							
	Temperature range II	-40 °C to +120 °C	(max. long term temperature +72 °C and max. short term temperature +120 °C)							
fischer injection system FIS V										
Intended Use Specifications (part 1)						Annex B 1				

Specifications of intended use (part 2)

Base materials:

- Reinforced or unreinforced normal weight concrete according to EN 206:2013
- Strength classes C20/25 to C50/60 according to EN 206:2013

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel)
- Structures subject to external atmospheric exposure, to permanently damp internal conditions or in other particular aggressive conditions (high corrosion resistant steel)

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used)

Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages under static or quasi-static actions are designed in accordance with EOTA Technical Report TR 029 "Design of bonded anchors" Edition September 2010 or CEN/TS 1992-4:2009

Installation:

- Anchor installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Anchorage depth should be marked and adhered to on installation
- Overhead installation is allowed


fischer injection system FIS V	
Intended Use Specifications (part 2)	Annex B 2

Table B2: Installation parameters for anchor rods

Size		M6	M8	M10	M12	M16	M20	M24	M27	M30		
Width across flats	SW	[mm]	10	13	17	19	24	30	36	41	46	
Nominal drill bit diameter	d_0		8	10	12	14	18	24	28	30	35	
Drill hole depth	h_0		$h_0 = h_{\text{ef}}$									
Effective anchorage depth	$h_{\text{ef,min}}$		50	60	60	70	80	90	96	108	120	
	$h_{\text{ef,max}}$		72	160	200	240	320	400	480	540	600	
Minimum spacing and minimum edge distance	$s_{\text{min}} = c_{\text{min}}$		40	40	45	55	65	85	105	125	140	
Diameter of clearance hole in the fixture ¹⁾	pre-positioned anchorage		7	9	12	14	18	22	26	30	33	
	push through anchorage		9	11	14	16	20	26	30	32	40	
Minimum thickness of concrete member	h_{min}		$h_{\text{ef}} + 30$ (≥ 100)				$h_{\text{ef}} + 2d_0$					
Maximum installation torque	$T_{\text{inst,max}}$	[Nm]	5	10	20	40	60	120	150	200	300	

¹⁾ For larger clearance holes in the fixture see TR 029, 4.2.2.1 or CEN/TS 1992-4-1:2009, 5.2.3.1

Anchor rod:



Marking (on random place) fischer anchor rod:

Property class 8.8, stainless steel, property class 80 or high corrosion resistant steel, property class 80: •
Stainless steel A4, property class 50 and high corrosion resistant steel, property class 50: ••
Or colour coding according to DIN 976-1

Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:

- Materials, dimensions and mechanical properties according Annex A 3, Table A1
- Inspection certificate 3.1 according to EN 10204:2004, the documents have to be stored
- Setting depth is marked

fischer injection system FIS V

Intended Use
Installation parameters anchor rods


Annex B 3

Table B3: Installation parameters for fischer internal threaded anchors RG MI

Size		M8	M10	M12	M16	M20	
Diameter of anchor	d_H	[mm]	12	16	18	22	28
Nominal drill bit diameter	d_0		14	18	20	24	32
Drill hole depth	h_0		$h_0 = h_{ef}$				
Effective anchorage depth ($h_{ef} = L_H$)	h_{ef}		90	90	125	160	200
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$		55	65	75	95	125
Diameter of clearance hole in the fixture ¹⁾	d_f		9	12	14	18	22
Minimum thickness of concrete member	h_{min}		120	125	165	205	260
Maximum screw-in depth	$l_{E,max}$		18	23	26	35	45
Minimum screw-in depth	$l_{E,min}$		8	10	12	16	20
Maximum installation torque	$T_{inst,max}$	[Nm]	10	20	40	80	120

¹⁾ For larger clearance holes in the fixture see TR 029, 4.2.2.1 or CEN/TS 1992-4-1:2009, 5.2.3.1

fischer internal threaded anchor RG MI



Retaining bolt or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Annex A 3, Table A1

fischer injection system FIS V

Intended Use

Installation parameters fischer internal threaded anchors RG MI


Annex B 4

Table B4: Installation parameters for reinforcing bars

Nominal diameter of the bar	Φ	8 ¹⁾	10 ¹⁾	12 ¹⁾	14	16	20	25	28			
Nominal drill bit diameter	d_0 [mm]	10	12	12	14	14	16	18	20	25	30	35
Drill hole depth		$h_0 = h_{\text{ef}}$										
Effective anchorage depth		60	60	70	75	80	90	100	112			
		160	200	240	280	320	400	500	560			
Minimum spacing and minimum edge distance		40	45	55	60	65	85	110	130			
Minimum thickness of concrete member	h_{min}	$h_{\text{ef}} + 30$ (≥ 100)			$h_{\text{ef}} + 2d_0$							

¹⁾ Both drill bit diameters can be used

Reinforcing bar



- The minimum value of related rib area $f_{R,\text{min}}$ must fulfil the requirements of EN 1992-1-1:2004+AC:2010
- The rib height must be within the range: $0,05 \cdot \Phi \leq h_{\text{rib}} \leq 0,07 \cdot \Phi$
(Φ = Nominal diameter of the bar, h_{rib} = rib height)


fischer injection system FIS V

Intended Use
Installation parameters reinforcing bars

Annex B 5

Table B5: Installation parameters for fischer rebar anchor FRA

Size		M12 ¹⁾	M16	M20	M24
Nominal diameter of the bar	ϕ	12	16	20	25
Width across flats	SW	19	24	30	36
Nominal drill bit diameter	d_0	14 16	20	25	30
Drill hole depth	h_0	$h_{\text{ef}} + l_e$			
Effective anchorage depth	$h_{\text{ef,min}}$	70	80	90	96
	$h_{\text{ef,max}}$	140	220	300	380
Distance concrete surface to welded join	l_e	100			
Minimum spacing and minimum edge distance	$s_{\min} = c_{\min}$	55	65	85	105
Diameter of clearance hole in the fixture ²⁾	pre-positioned $\leq d_f$ push through $\leq d_f$	14	18	22	26
Minimum thickness of concrete member	h_{\min}	18	22	26	32
Maximum installation torque	$T_{\text{inst,max}}$	[Nm]	40	60	120
			$h_0 + 2d_0$		
			$h_0 + 30$ (≥ 100)		

¹⁾ Both drill bit diameters can be used²⁾ For larger clearance holes in the fixture see TR 029, 4.2.2.1 or CEN/TS 1992-4-1:2009, 5.2.3.1**fischer rebar anchor FRA**

Marking frontal e.g.:


FRA (for stainless steel);
 FRA C (for high corrosion resistant steel)

fischer injection system FIS V

Intended Use
 Installation parameters rebar anchor FRA
Annex B 6

Table B6: Parameters of steel brush FIS BS Ø

Drill bit diameter	d_0	[mm]	8	10	12	14	16	18	20	24	25	28	30	35
Steel brush diameter	d_b		9	11	14	16	20		25	26	27	30		40

**Table B7:** Maximum processing time of the mortar and minimum curing time
(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

System temperature [°C]	Maximum processing time t_{work} [minutes]			Minimum curing time ¹⁾ t_{cure} [minutes]		
	FIS VW High Speed	FIS V	FIS VS Low Speed	FIS VW High Speed	FIS V	FIS VS Low Speed
-10 to -5	---	---	---	12 hours	---	---
> -5 to ±0	5	---	---	3 hours	24 hours	---
> ±0 to +5	5	13	---	3 hours	3 hours	6 hours
> +5 to +10	3	9	20	50	90	3 hours
> +10 to +20	1	5	10	30	60	2 hours
> +20 to +30	---	4	6	---	45	60
> +30 to +40	---	2	4	---	35	30

¹⁾ In wet concrete or flooded holes the curing times must be doubled







fischer injection system FIS V

Intended Use
Cleaning tools
Processing times and curing times

Annex B 7



Installation instructions part 1

Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Drill the hole. Drill hole diameter d_0 and drill hole depth h_0 see Tables B2, B3, B4, B5		
2		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18 \text{ mm}$ blow out the hole four times by hand		For $h_{ef} > 12d$ and / or $d_0 \geq 18 \text{ mm}$ blow out the hole four times with oil-free compressed air ($p \geq 6 \text{ bar}$)
3		Brush the drill hole four times. For deep holes use an extension. Corresponding brushes see Table B6		
4		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18 \text{ mm}$ blow out the hole four times by hand		For $h_{ef} > 12d$ and / or $d_0 \geq 18 \text{ mm}$ blow out the hole four times with oil-free compressed air ($p \geq 6 \text{ bar}$)

Go to step 5

Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see Table B1) for correct operation of the dust extraction
2		Use a suitable dust extraction system, e.g. Bosch GAS 35 M AFC or a comparable dust extraction system with equivalent performance data

Drill the hole with hollow drill bit. The dust extraction system has to extract the
drill dust nonstop during the drilling process. Diameter of drill hole d_0 and drill
hole depth h_0 see **Tables B2, B3, B4, B5**



Go to step 5

fischer injection system FIS V

Intended use
 Installation instructions part 1
Annex B 8




Installation instructions part 2

Preparing the cartridge

5		Remove the sealing cap Screw on the static mixer (the spiral in the static mixer must be clearly visible)
6		Place the cartridge into the dispenser
7		Extrude approximately 10 cm of material until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey

Go to step 8

Mörtelinjektion

8		Fill approximately 2/3 of the drill hole with mortar. Always begin from the bottom of the hole and avoid bubbles		For drill hole depth ≥ 150 mm use an extension tube		For overhead installation, deep holes $h_0 > 250$ mm or drill hole diameter $d_0 \geq 40$ mm use an injection-adapter
---	--	--	--	--	--	---

Go to step 9





fischer injection system FIS V

Intended use
Installation instructions part 2




Annex B 9

Installation instructions part 3

Installation of anchor rods or fischer internal threaded anchors RG MI

9		<p>Only use clean and oil-free anchor elements. Mark the setting depth of the anchor. Push the threaded rod or fischer internal threaded RG MI anchor down to the bottom of the hole, turning it slightly while doing so. After inserting the anchor element, excess mortar must be emerged around the anchor element. If not, pull out the anchor element immediately and reinject mortar.</p>
10	 <p>For overhead installations support the anchor rod with wedges. (e.g. fischer centering wedges)</p>	 <p>For push through installation fill the annular gap with mortar</p>
10	 <p>Wait for the specified curing time t_{cure} see Table B7</p>	 <p>Mounting the fixture $T_{inst,max}$ see Tables B2 and B3</p>

Installation reinforcing bars and fischer rebar anchor FRA

9		<p>Only use clean and oil-free reinforcing bars or fischer FRA. Mark the setting depth. Turn while using force to push the reinforcement bar or the fischer FRA into the filled hole up to the setting depth mark</p>
10		<p>When the setting depth mark is reached, excess mortar must be emerged from the mouth of the drill hole. If not, pull out the anchor element immediately and reinject mortar</p>
10	 <p>Wait for the specified curing time t_{cure} see Table B7</p>	 <p>Mounting the fixture $T_{inst,max}$ see Table B5</p>

fischer injection system FIS V

Intended use
Installation instructions part 3

Annex B 10

Table C1: Characteristic values for the **steel bearing capacity** under tensile / shear load of **fischer anchor rods** and **standard threaded rods**

Size			M6	M8	M10	M12	M16	M20	M24	M27	M30		
Bearing capacity under tensile load, steel failure													
Charact.bearing capacity $N_{Rk,s}$	Property class	[kN]	5.8	10	19	29	43	79	123	177	230		
			8.8	16	29	47	68	126	196	282	368		
			50	10	19	29	43	79	123	177	230		
			70	14	26	41	59	110	172	247	322		
			80	16	30	47	68	126	196	282	368		
											449		
Partial safety factors¹⁾													
Partial safety factor $\gamma_{Ms,N}$	Property class	[-]	5.8								1,50		
			8.8								1,50		
			50								2,86		
			70								1,50 ²⁾ / 1,87		
			80								1,60		
Bearing capacity under shear load, steel failure													
without lever arm													
Charact.bearing capacity $V_{Rk,s}$	Property class	[kN]	5.8	5	9	15	21	39	61	89	115		
			8.8	8	15	23	34	63	98	141	184		
			50	5	9	15	21	39	61	89	115		
			70	7	13	20	30	55	86	124	161		
			80	8	15	23	34	63	98	141	184		
											225		
with lever arm													
Charact. bending moment	Property class	[Nm]	5.8	7	19	37	65	166	324	560	833		
			8.8	12	30	60	105	266	519	896	1333		
			50	7	19	37	65	166	324	560	833		
			70	10	26	52	92	232	454	784	1167		
			80	12	30	60	105	266	519	896	1333		
											1797		
Partial safety factors¹⁾													
Partial safety factor $\gamma_{Ms,V}$	Property class	[-]	5.8								1,25		
			8.8								1,25		
			50								2,38		
			70								1,25 ²⁾ / 1,56		
			80								1,33		
¹⁾ In absence of other national regulations													
²⁾ Only admissible for steel C, with $f_{yk} / f_{uk} \geq 0,8$ and $A_5 > 12\%$ (e.g. fischer anchor rods)													
fischer injection system FIS V													
Performances Characteristic steel bearing capacity of fischer anchor rods and standard threaded rods										Annex C 1			

Table C2: Characteristic values for the **steel bearing capacity** under tensile / shear load of **fischer internal threaded anchors RG MI**

Size	M8	M10	M12	M16	M20	
Bearing capacity under tensile load, steel failure						
Characteristic bearing capacity $N_{Rk,s}$ with screw	Property class 5.8	[kN]	19	29	43	
	Property class 8.8		29	47	68	
	Property class A4		26	41	59	
	Property class 70		26	41	59	
Partial safety factors¹⁾						
Partial safety factor $\gamma_{Ms,N}$	Property class 5.8	[-]	1,50			
	Property class 8.8		1,50			
	Property class A4		1,87			
	Property class 70		1,87			
Bearing capacity under shear load, steel failure						
without lever arm						
Characteristic bearing capacity $V_{Rk,s}$ with screw	Property class 5.8	[kN]	9,2	14,5	21,1	
	Property class 8.8		14,6	23,2	33,7	
	Property class A4		12,8	20,3	29,5	
	Property class 70		12,8	20,3	29,5	
with lever arm						
Characteristic bending moment $M_{Rk,s}^0$ with screw	Property class 5.8	[Nm]	20	39	68	
	Property class 8.8		30	60	105	
	Property class A4		26	52	92	
	Property class 70		26	52	92	
Partial safety factors¹⁾						
Partial safety factor $\gamma_{Ms,V}$	Property class 5.8	[-]	1,25			
	Property class 8.8		1,25			
	Property class A4		1,56			
	Property class 70		1,56			

¹⁾ In absence of other national regulations²⁾ Only for steel failure without lever arm

fischer injection system FIS V

Performances

Characteristic steel bearing capacity of fischer internal threaded anchors RG MI

Annex C 2

Table C3: Characteristic values for the **steel bearing capacity** under tensile / shear load of **reinforcing bars**

Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28
Bearing capacity under tensile load, steel failure									
Characteristic bearing capacity	$N_{Rk,s}$ [kN]								$A_s \cdot f_{uk}^{1)}$
Bearing capacity under shear load, steel failure									
without lever arm									
Characteristic bearing capacity	$V_{Rk,s}$ [kN]								$0,5 \cdot A_s \cdot f_{uk}^{1)}$
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	k_2	[-]							0,8
with lever arm									
Characteristic bending moment	$M_{Rk,s}^0$ [Nm]								$1,2 \cdot W_{el} \cdot f_{uk}^{1)}$

¹⁾ f_{uk} or f_{yk} respectively must be taken from the specifications of the reinforcing bar

Table C4: Characteristic values for the **steel bearing capacity** under tensile / shear load of **fischer rebar anchors FRA**

Size		M12	M16	M20	M24
Bearing capacity under tensile load, steel failure					
Characteristic bearing capacity	$N_{Rk,s}$ [kN]	63	111	173	270
Partial safety factors¹⁾					
Partial safety factor	$\gamma_{Ms,N}$ [-]				1,4
Bearing capacity under shear load, steel failure					
without lever arm					
Characteristic bearing capacity	$V_{Rk,s}$ [kN]	30	55	86	124
with lever arm					
Characteristic bearing capacity	$M_{Rk,s}^0$ [Nm]	92	233	454	785
Partial safety factors¹⁾					
Partial safety factor	$\gamma_{Ms,V}$ [-]				1,56

¹⁾ In absence of other national regulations

fischer injection system FIS V

Performances

Characteristic steel bearing capacity of reinforcing bars and fischer rebar anchors FRA

Annex C 3

Table C5: General design factors for the bearing capacity under tensile / shear load; uncracked or cracked concrete

Size			All sizes							
Bearing capacity under tensile load										
Factors acc. to CEN/TS 1992-4:2009 Section 6.2.2.3										
Uncracked concrete k_{ucr}										
	[$-$]			10,1						
Cracked concrete k_{cr}				7,2						
Factors for the compressive strength of concrete > C20/25										
Increasing factor for τ_{Rk}	Ψ_c	[$-$]	C25/30	1,05						
			C30/37	1,10						
			C35/45	1,15						
			C40/50	1,19						
			C45/55	1,22						
			C50/60	1,26						
Splitting failure										
Edge distance	$c_{cr,sp}$	[mm]	$h / h_{ef} \geq 2,0$	1,0 h_{ef}						
			$2,0 > h / h_{ef} > 1,3$	4,6 h_{ef} - 1,8 h						
			$h / h_{ef} \leq 1,3$	2,26 h_{ef}						
Spacing	$s_{cr,sp}$			2 $c_{cr,sp}$						
Concrete cone failure acc. to CEN/TS 1992-4-5:2009 Section 6.2.3.2										
Edge distance	$c_{cr,N}$	[mm]		1,5 h_{ef}						
Spacing	$s_{cr,N}$			2 $c_{cr,N}$						
Bearing capacity under shear load										
Installation safety factors										
All installation conditions	$\gamma_2 = \gamma_{inst}$	[$-$]		1,0						
Concrete pry-out failure										
Factor k acc. to TR029 Section 5.2.3.3 resp. k_3 acc. to CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$	[$-$]		2,0						
Concrete edge failure										
The value of h_{ef} (= l_f) under shear load		[mm]	min (h_{ef} ; 8d)							
Calculation diameters										
Size		M6	M8	M10	M12	M16	M20	M24	M27	M30
fischer anchor rods and standard threaded rods		6	8	10	12	16	20	24	27	30
fischer internal threaded anchors RG MI		[mm]	---	12	16	18	22	28	---	---
fischer rebar anchors FRA		d	---	---	---	12	16	20	25	---
Nominal diameter of the bar		ϕ	8	10	12	14	16	20	25	28
Reinforcing bar		d	[mm]	8	10	12	14	16	20	25
fischer injection system FIS V										
Performances					Annex C 4					
General design factors relating to the characteristic bearing capacity under tensile / shear load										

Table C6: Characteristic values of resistance for fischer anchor rods and standard threaded rods in hammer drilled holes; uncracked or cracked concrete

Size	M6	M8	M10	M12	M16	M20	M24	M27	M30							
Combined pullout and concrete cone failure																
Calculation diameter d [mm]	6	8	10	12	16	20	24	27	30							
Uncracked concrete																
Characteristic bond resistance in uncracked concrete C20/25																
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)																
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$ [N/mm ²]	9,0 6,5	11,0 9,5	11,0 9,5	11,0 9,0	10,0 8,5	9,5 8,0	9,0 7,5	8,5 7,0						
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole) ¹⁾																
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$ [N/mm ²]	---	---	---	9,5 7,5	8,5 7,0	8,0 6,5	7,5 6,0	7,0 6,0						
Installation safety factors																
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[\cdot]	1,0													
Flooded hole	$\gamma_2 = \gamma_{inst}$	[\cdot]	---													
Cracked concrete																
Characteristic bond resistance in cracked concrete C20/25																
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)																
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,cr}$ [N/mm ²]	---	---	6,0 5,0	6,0 5,0	6,0 5,0	5,5 5,0	4,5 4,0	4,0 3,5						
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole) ¹⁾																
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,cr}$ [N/mm ²]	---	---	---	5,0 4,0	5,0 4,0	4,5 4,0	4,0 3,5	3,5 3,0						
Installation safety factors																
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[\cdot]	1,0													
Flooded hole	$\gamma_2 = \gamma_{inst}$	[\cdot]	---													
¹⁾ Only with coaxial cartridges: 380 ml, 400 ml, 410 ml																
fischer injection system FIS V																
Performances Characteristic values for static or quasi-static action under tensile load for fischer anchor rods and standard threaded rods (uncracked or cracked concrete)								Annex C 5								

Table C7: Characteristic values of resistance for fischer internal threaded anchors RG MI in hammer drilled holes; uncracked concrete

Size	M8	M10	M12	M16	M20		
Combined pullout and concrete cone failure							
Calculation diameter d [mm]	12	16	18	22	28		
Uncracked concrete							
Characteristic bond resistance in uncracked concrete C20/25							
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)							
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,5 9,0	10,0 8,0	9,5 8,0	9,0 7,5	8,5 7,0
Hammer-drilling with standard drill bit or hollow drill bit (flooded hole) ¹⁾							
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,0 7,5	9,0 6,5	9,0 6,5	8,5 6,0	8,0 6,0
Installation safety factors							
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[\cdot]	1,0				
Flooded hole			1,2 ¹⁾				

¹⁾ Only with coaxial cartridges: 380 ml, 400 ml, 410 ml

fischer injection system FIS V

Performances

Characteristic values for static or quasi-static action under tensile load for fischer internal threaded anchors RG MI (uncracked concrete)

Annex C 6

Table C8: Characteristic values of resistance for reinforcing bars in hammer drilled holes; uncracked or cracked concrete

Nominal diameter of the bar	ϕ	8	10	12	14	16	20	25	28		
Combined pullout and concrete cone failure											
Calculation diameter	d [mm]	8	10	12	14	16	20	25	28		
Uncracked concrete											
Characteristic bond resistance in uncracked concrete C20/25											
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)											
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$	[N/mm ²]	11,0 9,5	11,0 9,5	11,0 9,0	10,0 8,5	10,0 8,5	9,5 8,0	9,0 7,5	8,5 7,0
Installation safety factor											
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[-]					1,0				
Cracked concrete											
Characteristic bond resistance in cracked concrete C20/25											
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)											
Temperature range	I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,cr}$	[N/mm ²]	-- --	3,0 3,0	5,0 4,5	5,0 4,5	5,0 4,5	4,5 4,0	4,0 3,5	4,0 3,5
Installation safety factor											
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[-]					1,0				

fischer injection system FIS V

Performances

Characteristic values for static or quasi-static action under tensile load for reinforcing bars (uncracked or cracked concrete)

Annex C 7

Table C9: Characteristic values of resistance for fischer rebar anchors FRA in hammer drilled holes; uncracked or cracked concrete

Size	M12	M16	M20	M24	
Combined pullout and concrete cone failure					
Calculation diameter d [mm]	12	16	20	25	
Uncracked concrete					
Characteristic bond resistance in uncracked concrete C20/25					
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)					
Temperature range I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,ucr}$ [N/mm ²]	11,0 9,0	10,0 8,5	9,5 8,0	9,0 7,5
Installation safety factor					
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[-]	1,0		
Cracked concrete					
Characteristic bond resistance in cracked concrete C20/25					
Hammer-drilling with standard drill bit or hollow drill bit (dry and wet concrete)					
Temperature range I: 50 °C / 72 °C II: 72 °C / 120 °C	$\tau_{Rk,cr}$ [N/mm ²]	5,0 4,5	5,0 4,5	4,5 4,0	4,0 3,5
Installation safety factor					
Dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[-]	1,0		

fischer injection system FIS V

Performances

Characteristic values for static or quasi-static action under tensile load for fischer rebar anchors FRA (uncracked or cracked concrete)

Annex C 8

Table C10: Displacements for anchor rods

Size	M6	M8	M10	M12	M16	M20	M24	M27	M30
Displacement-Factors for tensile load¹⁾									
Uncracked concrete; Temperature range I, II									
δ_{N0} -Faktor	[mm/(N/mm ²)]	0,09	0,09	0,09	0,10	0,10	0,10	0,11	0,12
$\delta_{N\infty}$ -Faktor		0,10	0,10	0,10	0,12	0,12	0,12	0,13	0,14
Cracked concrete; Temperature range I, II									
δ_{N0} -Faktor	[mm/(N/mm ²)]	---	---	0,12	0,12	0,13	0,13	0,14	0,15
$\delta_{N\infty}$ -Faktor		---	---	0,27	0,30	0,30	0,35	0,35	0,40
Displacement-Factors for shear load²⁾									
Uncracked or cracked concrete; Temperature range I, II									
δ_{V0} -Faktor	[mm/kN]	0,11	0,11	0,11	0,10	0,10	0,09	0,09	0,08
$\delta_{V\infty}$ -Faktor		0,12	0,12	0,12	0,11	0,11	0,10	0,09	0,09

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed}: Design value of the applied tensile stress)²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed}: Design value of the applied shear force)**Table C11: Displacements for fischer internal threaded anchors RG MI**

Size	M8	M10	M12	M16	M20
Displacement-Factors for tensile load¹⁾					
Uncracked concrete; Temperature range I, II					
δ_{N0} -Faktor	[mm/(N/mm ²)]	0,10	0,11	0,12	0,13
$\delta_{N\infty}$ -Faktor		0,13	0,14	0,15	0,16
Displacement-Factors for shear load²⁾					
Uncracked concrete; Temperature range I, II					
δ_{V0} -Faktor	[mm/kN]	0,12	0,12	0,12	0,12
$\delta_{V\infty}$ -Faktor		0,14	0,14	0,14	0,14

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed}: Design value of the applied tensile stress)²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed}: Design value of the applied shear force)

fischer injection system FIS V

Performances

Displacements for anchor rods and fischer internal threaded anchors RG MI

Annex C 9

Table C12: Displacements for reinforcing bars

Nominal diameter of the bar ϕ	8	10	12	14	16	20	25	28
Displacement-Factors for tensile load¹⁾								
Uncracked concrete; Temperature range I, II								
δ_{N0} -Faktor [mm/(N/mm ²)]	0,09	0,09	0,10	0,10	0,10	0,10	0,10	0,11
$\delta_{N\infty}$ -Faktor	0,10	0,10	0,12	0,12	0,12	0,12	0,13	0,13
Cracked concrete; Temperature range I, II								
δ_{N0} -Faktor [mm/(N/mm ²)]	---	0,12	0,12	0,13	0,13	0,13	0,13	0,14
$\delta_{N\infty}$ -Faktor	---	0,27	0,30	0,30	0,30	0,30	0,35	0,37
Displacement-Factors for shear load²⁾								
Uncracked or cracked concrete; Temperature range I, II								
δ_{V0} -Faktor [mm/kN]	0,11	0,11	0,10	0,10	0,10	0,09	0,09	0,08
$\delta_{V\infty}$ -Faktor	0,12	0,12	0,11	0,11	0,11	0,10	0,10	0,09

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed}: Design value of the applied tensile stress)²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed}: Design value of the applied shear force)**Table C13: Displacements for fischer rebar anchors FRA**

Size	M12	M16	M20	M24
Displacement-Factors for tensile load¹⁾				
Uncracked concrete; Temperature range I, II				
δ_{N0} -Faktor [mm/(N/mm ²)]	0,10	0,10	0,10	0,10
$\delta_{N\infty}$ -Faktor	0,12	0,12	0,12	0,13
Cracked concrete; Temperature range I, II				
δ_{N0} -Faktor [mm/(N/mm ²)]	0,12	0,13	0,13	0,13
$\delta_{N\infty}$ -Faktor	0,30	0,30	0,30	0,35
Displacement-Factors for shear load²⁾				
Uncracked or cracked concrete; Temperature range I, II				
δ_{V0} -Faktor [mm/kN]	0,10	0,10	0,09	0,09
$\delta_{V\infty}$ -Faktor	0,11	0,11	0,10	0,10

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed}: Design value of the applied tensile stress)²⁾ Calculation of effective displacement:

$$\delta_{V0} = \delta_{V0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed}: Design value of the applied shear force)

fischer injection system FIS V

Performances

Displacements for reinforcing bars and fischer rebar anchors FRA

Annex C 10